Raman Scattering Spectra of Boron Imidazolate Frameworks Containing Different Magnetic Ions

Jackson Davis,¹ Soumyodip Banerjee,² Pilar Beccar-Varela,² V. Sara Thoi,^{2, 3} and Natalia Drichko¹ ¹⁾Department of Physics and Astronomy, Johns Hopkins University, Baltimore, Maryland 21218,

USA

²⁾Department of Chemistry, Johns Hopkins University, Baltimore, Maryland 21218, USA

³⁾Department of Materials Science and Engineering, Johns Hopkins University, Baltimore, Maryland 21218, USA

(*Electronic mail: drichko@jhu.edu)

(Dated: 28 March 2023)

We present a Raman scattering spectroscopic study of boron imidazolate metal-organic frameworks (BIFs) with three different magnetic metal ions and one non-magnetic in a wide frequency range from 25 to 1700 cm⁻¹, which covers local vibrations of the linkers and well as collective lattice vibrations. We show that the spectral region above 800 cm^{-1} belongs to the local vibrations of the linkers, which have the same frequencies for the studied BIFs without any dependence on the structure of the BIFs, and are easily interpreted based on the spectra of imidazolate linkers. In contrast, collective lattice vibrations, observed below 100 cm^{-1} , show a distinction between cage and two-dimensional BIFs structures, with a weak dependence on the metal node. We identify the range of vibrations around 200 cm⁻¹, which are distinct for each MOF, depending on a metal node. Our work demonstrates the energy hierarchy in the vibrational response of BIFs.

I. INTRODUCTION

Much of the study of metal-organic frameworks (MOFs) in recent years has focused on their tunability and porosity. Since MOF structures can include magnetic ions or clusters connected by organic linkers, the possibility of achieving interesting magnetic states in MOFs has been discussed^{1,2}. However, most of the recent studies of magnetic properties in MOFs have been limited by basic magnetization and magnetic susceptibility measurements. In order to study magnetism in these materials we will need to employ spectroscopy, such as magnetic Raman scattering. In fact, magnetic Raman scattering has demonstrated its ability to probe the spectrum of magnetic excitations in organic magnetic materials^{3,4} where magnetic neutron scattering is challenging due to weak signals and presence of hydrogen in the materials. In order to use Raman scattering spectroscopy as a tool to study different MOF structures and their magnetic response, we need to obtain information about the energy scales of all the other excitations; we must identify what part of the acquired spectroscopic information is related to the collective lattice modes, and what part is related to the linker vibrations. Vibrational Raman scattering has been widely used as a characterization tool for MOFs, as the vibrational modes within the organic ligands, and between the ligands and the metal ions, tend to produce strong peaks in the Raman spectra⁵. In this manuscript, we present our vibrational Raman scattering studies of a range of MOFs which share the same linkers, but include different transitional metal ions and show three different structures. We aim to understand the hierarchy of the energy scales we observe in the very rich spectra of MOFs, and develop an efficient way to interpret the spectral features.

All MOF materials studied here belong to the class of boron imidazolate frameworks (BIFs), which consist of metal ions coordinated by a boron imidazolate ligand. We present Raman spectra of four different BIFs with magnetic ions Cu^{2+} (S= 1/2), Ni²⁺ (S=1), Co²⁺ (S= 3/2) and non-magnetic Zn²⁺ as the metal cations. These BIFs have three distinct structures: Cu-BIF and Zn-BIF each possesses one of two cagelike structures^{6,7}, while Co-BIF and Ni-BIF are isostructural, possessing a layered 2D triangular lattice⁸. The cage BIFs have topologies similar to zeolites and zeolitic imidazolate frameworks (ZIFs). In ZIFs, each metal cation bonds to one nitrogen of four different imidazolate rings, creating a tetrahedral metal environment, and these linked tetrahedra form a porous 3D network of connected cages⁹. In cage BIFs, one N on the imidazolate ring binds to a metal cation, while the other binds to a B^{3+} cation. For instance, in the cage Cu-BIF, pictured in Fig. 1, the metal cations have an environment of four coplanar N atoms from four different imidazolate rings, while one oxygen from one H₂O weakly binds to the metal in the out-of-plane direction, creating a low symmetry environment for the metal atom compared to standard inorganic oxides. The Zn-BIF, pictured in Fig. 2, is composed of smaller cages of 4 Zn and 4 boron imidazolate ligands, and exhibits an anisotropic tetrahedral Zn environment.

In 2D layered BIFs, no cages are formed at all, and metal ions arrange in a 2D triangular lattice (see Co octahedra in Fig. 3), which is layered along the crystallographic c axis in the bulk. In these BIFs, as illustrated for Co-BIF, metal ions are found in an octahedral environment, as the metal binds to a N atom on 6 imidazolate rings, as shown in Fig. 3.

The boron cations connect three of these metal-imidazolate complexes, as seen in Fig. 1. Because of this, the exchange path between metal centers is through not only one imidazolate ring, as in ZIFs, but follows an extended Me-Im-B-Im-Me path, in both cage and 2D BIFs. This extended exchange path leads to low magnetic exchange between magnetic metal centers, if any at all . While the cage Cu-BIF MOF shows magnetic interactions close to zero, weak magnetic interactions have been detected in 2D layered BIFs¹⁰.

We show that we can identify the linker vibrations that are



FIG. 1. Left panel: Cu-BIF cage structure¹¹. Note the 4-membered ring structure of the pore. Right panel: anisotropic square pyramidal Cu environment. H atoms omitted for clarity, except those on H_2O that bind to Cu. All structural models visualized in VESTA¹².



FIG. 2. Left panel: Zn-BIF cage structure⁷. Note the preserved 4membered ring structure of the pore, while the structure of the cage is different from Cu-BIF. Right panel: anisotropic tetrahedral Zn environment. H atoms omitted for clarity, except those on H_2O that bind to Zn.

independent of the metal ions and their environment, while the vibrations of the metal environment itself are sensitive to the substitution of a metal atom. Despite the differences in crystal structures, the Raman vibrations of the imidazolate linkers observed above 800 cm^{-1} are similar for these MOFs. In contrast, the lattice vibrations observed below 100 cm^{-1} are fingerprints of the structure. The intermediate frequencies in the range of $100-300 \text{ cm}^{-1}$ belong to the Raman vibrations of the metal environment and depend on the metal cation. These results demonstrate the distinct energy scales of vibrations of MOFs of different origins. This fact allows for an easy interpretation of the vibrational features of these compounds.



FIG. 3. Left panel: Triangular lattice structure of Co-BIF in (ab) layer⁸. Right panel: octahedral Co environment. H atoms omitted for clarity. Ni-BIF is isostructural to Co-BIF⁸

II. EXPERIMENTAL

MOFs were synthesized following reported literature procedures for Zn-BIF⁷, Cu-BIF¹¹, and Co and Ni-BIF⁸.

Raman spectra were measured using a micro-Raman option of a T64000 Horiba-Jobin-Yvon spectrometer equipped with an Olympus microscope and a LN₂ cooled CCD. Spectra were excited with the 514.5 nm line of a Coherent Innova 70C laser, with the power kept below 500 μ W for a probe of 2 μ m in diameter to avoid heating the sample. Spectra were measured at room temperature with a spectral resolution of 2 cm⁻¹ (low-energy region) and 6 cm⁻¹ (Ni, Zn, and Cu in high energy region).

Intensity of Raman spectra for different materials were normalized on the laser power, grating reflectance, and size of the slit. Background signals of stray laser light were subtracted manually from the low-frequency Co, Cu, and Ni-BIF spectra to highlight the narrow vibrational mode peaks. A Lorentzian peak centered at 0 cm⁻¹ was used to approximately model the background to be subtracted. In Zn-BIF, a broad photoluminescent background was subtracted by comparison to the spectra of pure imidazolate containing an identical background. To compare Raman scattering intensities of measured BIFs vibrational spectra shown in the figures are additionally normalized to the v(CN) modes in the 1200-1250 cm⁻¹ range, as a result intensity of Raman spectra $I(\omega)$ were multiplied by a constant c_1 , where $c_1 = 6.5$ for Zn-BIF, $c_1 = 16$ for Co-BIF, and $c_1 = 10$ for Cu-BIF. Similarly, low-frequency spectra were multiplied by a constant c_2 to highlight lattice modes below 100 cm⁻¹, where $c_2 = 2.5$ for Zn-BIF, $c_2 = 6.5$ for Co-BIF, and $c_2 = 10$ for Cu-BIF.

III. RESULTS AND DISCUSSION

Measured Raman spectra of Co-BIF, Cu-BIF, Ni-BIF, and Zn-BIF are shown in two different regions in Figs. 4 and 5. The 500-1700 cm⁻¹ region in Fig. 4 contains the expected vibrational modes of imidazolate and allows for preliminary band assignments, which are summarized in Table I. The 0-500 cm⁻¹ region in Fig. 5 contains low-energy lattice modes below 100 cm⁻¹ and vibrational modes of metal environments above.

The Raman vibrations of imidazolate linkers are expected in the 800-1600 cm⁻¹ spectral range based on assigned Raman spectra of ZIF-8⁵. Raman spectra of the four different BIFs have very similar frequencies of the majority of the molecular vibrations of the imidazolate ligand, despite the fact that they have three different crystal structures and four different metal nodes. This is in agreement with the expectation that the internal structure of the ligand remains unchanged between these MOFs. A comparison to previously reported Raman scattering spectra of ZIF-8⁵ reveals a direct correspondence between molecular vibrations of imidazolate in ZIF and BIF structures and is taken as a basis for our interpretation of the vibrational spectra of BIFs. Table I summarizes the frequencies of 8 molecular vibrations, which are consistent with previously reported band assignments for imidazolate ligand.



FIG. 4. Raman spectra of Cu-, Co-, Zn-, and Ni-based BIFs in the range of ligand vibrational modes.

We mark these assignments in the Raman spectra of the BIFs shown in Fig. 4.

The most intense modes in the spectral region of 800-1000 $\rm cm^{-1}$ are bending vibrations of C-H bonds, which are out-ofplane with respect to the plane of the imidazolate ring. These three bands are found at very similar frequencies for all measured BIFs and close to the reported frequencies in ZIF-8. The C-H bonds are the farthest away from the metals, so one would expect that their frequencies are not strongly dependent on the metal nodes.

The spectral range between 1000 and 1500 cm⁻¹ contains 4 stretching vibrations of C-N bonds as well as a wagging vibration of N-H. Though the positions of the two lowest bands are shifted by 70 cm^{-1} to higher frequencies compared with the ZIF-8 spectra, the spacing of 40 cm^{-1} between them and their relative intensities are consistent with reported ZIF spectra. The C-N stretching vibration in the range from 1334-1343 cm^{-1} displays a shift to lower frequencies of 50 cm⁻¹. These differences between ZIF and BIF C-N vibrations can be attributed to the fact that the two N on an imidazolate ring bind to one metal ion and one B, rather than two Zn ions as in ZIFs. Hence, the molecular vibrations that involve the N are expected to differ qualitatively between ZIF and BIF spectra, though not between BIFs themselves. In contrast, other molecular vibrations (such as C-H bending) display more consistency between ZIF and BIF spectra due to their relative isolation from the environment external to the imidazolate ring.

The reported bending vibration of the methyl group in ZIF-8 is absent in BIF spectra since the imidazolate rings in the BIFs have no capping methyl group. The total suppression of the strong imidazolate ring breathing mode, found at 683 cm^{-1} in ZIF-8, can be a result of the lower symmetry (the absence of mirror symmetry) in the linker in BIF structures, which comes from imidazolate binding to one B and one metal ion, rather than two metal ions as in ZIFs. Alternatively, the suppression of this mode could be a result of a reduction

TABLE I. Frequencies of Raman active vibrations of ZIF-8⁵ linkers compared to that of Co, Cu, Zn, and Ni-BIF. Assignment of the modes is based on the assignment of the Raman spectra of ZIF-8⁵. δ : bend, v: stretch, ω : wag. All frequencies are listed in cm⁻¹. δ (CH) are out-of-plane with respect to the imidazolate plane.

Raman Mode	ZIF-8	Co-BIF	Cu-BIF	Zn-BIF	Ni-BIF
δ (CH)	834	831	853	weak	841
δ (CH) (C4-C5)	945	939	946	960	945
δ (CH) (C2)	1023	1018	1020	1021	1021
v(C5-N)	1143	1214	1215	1216	1210
v(C-N)	1182	1258	1252	1259	1247
ω (N-H)	1312	1316	1314	1311	1309
v(C5-N)	1385	1343	1335	1333	1336
v(C2-N)	1507	1505	1515	1517	1510

of electronic density on the imidazolate ring.

The spectral range of 100-300 cm^{-1} is the region of metalligand vibrations. The frequencies of these vibrations should be dependent both on the metal and on its coordination¹³. In particular, literature data suggest stretching vibrations of Cu-N in the octahedral environment at 280-290 cm^{-1} , and Zn in a tetrahedral environment at 207 cm⁻¹.¹³ Modes in this region therefore belong to the N-metal vibration, and have frequencies which depend on the metal ion. Zn-BIF has one mode at 181 cm⁻¹, while Co, Cu, and Ni have four weak modes at frequencies summarized in Table II. The similarity between Ni and Co-BIF N-metal vibrations is consistent with the identical octahedral environments or Ni and Co, with the small shift in frequencies potentially arising from a change in electronic density on the N atoms in the metal environment. The more significant differences in this region in the Cu and Zn-BIF spectra are consistent with their unique metal environments.

Co-BIF	Cu-BIF	Ni-BIF
136	129	148
175	151	193
188	169	205
248	263	252

TABLE II. Frequencies for four metal-N vibrational modes in the 100-300 cm⁻¹ region. Zn-BIF not included due to the lack of four clear mode in this region. All frequencies given in cm⁻¹.

Fig. 5 presents the low frequency spectra of the BIF MOFs. Typically for molecular crystals the region below 100 cm⁻¹ corresponds to lattice vibrations, which would depend on the structure of the MOFs. While to the best of our knowledge, there is no spectroscopic information on the lattice modes of BIFs, the lattice "collective" modes of ZIFs were studied to some extent by THz spectroscopy, neutron scattering, and DFT calculations, and were also found below 100 cm⁻¹.^{14,15}

In our experimental data, we find that two low-frequency vibrations of the cage Cu and Zn-BIFs occur at similar frequencies, while 2D Ni and Co-BIFs have similar lowfrequency spectra, distinct from the cage BIFs (see Table III). This demonstrates a distinct dependence of the lattice mode spectra on the structure of the MOFs, showing that the lattice



FIG. 5. Raman spectra of Cu-, Co-, Zn-, and Ni-based BIFs in the low energy region.

vibrations are fingerprints of a particular lattice structure, and not the chemical environment. We find that two of the lattice modes observed in the spectra for the two cage BIFs, Cu and Zn, are similar to Raman-active THz modes in the calculated DFT spectra of ZIF-8, which is also composed of a porous cage-like structure. These include a strong mode at 33.36 cm⁻¹, assigned to a symmetric 4-membered ring (see Fig. 1,2) gate opening, and a mode at 64.61 cm⁻¹, assigned to a 4-membered ring shearing¹⁴.

ZIF-8 DFT (cm^{-1})	Zn-BIF	Cu-BIF	Co-BIF	Ni-BIF
ring gate opening (33.36)	34	35	—	_
_	—	—	52	53
ring shearing (64.61)	62	58	—	—
_	_	_	77	74

TABLE III. Frequencies of observed modes below 100 cm^{-1} for the four BIFs.

The 2D layered BIFs, on the other hand, do not display any similarity to calculated THz modes of ZIFs, which is consistent with the significant structural differences between the 2D triangular lattice structure and the various cage structures. DFT calculations on the 2D structures are necessary to further interpret these vibrations.

IV. CONCLUSIONS

In this work we have presented Raman scattering spectra of BIF MOFs with different metal ions in a frequency range between 30 and 2000 cm⁻¹ and demonstrated a separation between the energy scales related to the different types of vibrations of the MOFs. The high frequency region of the spectra contains Raman-active vibrational modes of imidazolate ligands, which are similar between four different BIFs with different structures and metal nodes. They can be assigned based on the literature data of MOFs with the same linker molecules, ZIFs.

The low-energy region of the spectra demonstrates a consistency in lattice modes of isostructural BIFs. The modes of the cage BIFs have frequencies similar to the calculated lattice modes for ZIFs, while 2D BIFs have a distinctly different lattice mode spectrum. These results demonstrate that the lattice vibrations of MOFs are fingerprint of a certain structure.

The spectral region between approximately 100 and 300 $\rm cm^{-1}$ is dominated by the vibrations of the metal environment. The frequencies of vibrations observed in this region depend on the metal atom, but show some consistency between BIFs with different metals in the same environment.

The consistency of lattice modes and ligand vibrations provides an efficient way to understand and assign the spectra of MOFs without performing full calculations of the vibrational response of each MOF structure.

ACKNOWLEDGMENTS

Acknowledgement is made to the donors of the American Chemical Society Petroleum Research Fund for partial support of this research. We acknowledge the support of NSF Award No. DMR-2004074. S. B., P. B.-V., and V. S. T. acknowledge support by the U.S. Department of Energy (DOE), Office of Science, Office of Basic Energy Sciences, Catalysis Science program, under Award DE-SC0021955. P. B-V. thanks the Dean's ASPIRE grant from the Office of Undergraduate Research, Scholarly and Creative Activity at Johns Hopkins University. We further acknowledge Professor Tyrel McQueen, Dr. Veronica Stewart (Department of Chemistry, Johns Hopkins University), Chris Lygouras, and Peter Orban (Department of Physics and Astronomy, Johns Hopkins University) for their assistance in obtaining magnetic susceptibility and magnetization data.

DATA AVAILABILITY STATEMENT

The data that support the findings of this study are available from the corresponding author upon reasonable request.

CONFLICT OF INTEREST

The authors have no conflicts to disclose.

- ¹A. E. Thorarinsdottir and T. D. Harris, "Metal–Organic Framework Magnets," Chem. Rev. **120**, 8716–8789 (2020).
- ²G. Mínguez Espallargas and E. Coronado, "Magnetic functionalities in MOFs: From the framework to the pore," Chem. Soc. Rev. **47**, 533–557 (2018).
- ³N. Drichko, R. Hackl, and J. A. Schlueter, "Antiferromagnetic fluctuations in a quasi-two-dimensional organic superconductor detected by raman spectroscopy," Phys. Rev. B **92**, 161112 (2015).

- ⁴N. Hassan, S. Cunningham, M. Mourigal, E. I. Zhilyaeva, S. A. Torunova, R. N. Lyubovskaya, J. A. Schlueter, and N. Drichko, "Evidence for a quantum dipole liquid state in an organic quasi-two-dimensional material," Science **360**, 1101–1104 (2018).
- ⁵K. I. Hadjiivanov, D. A. Panayotov, M. Y. Mihaylov, E. Z. Ivanova, K. K. Chakarova, S. M. Andonova, and N. L. Drenchev, "Power of Infrared and Raman Spectroscopies to Characterize Metal-Organic Frameworks and Investigate Their Interaction with Guest Molecules," Chem. Rev. **121**, 1286–1424 (2021).
- ⁶D.-X. Zhang, H.-X. Zhang, H.-Y. Li, T. Wen, and J. Zhang, "Self-Assembly of Metal Boron Imidazolate Cages," Crystal Growth & Design **15**, 2433–2436 (2015).
- ⁷T. Wen and J. Zhang, "Rational design of metal boron imidazolate cages to frameworks," Inorganica Chimica Acta Next Generation, **460**, 89–92 (2017).
- ⁸S. Banerjee, X. Han, M. A. Siegler, E. M. Miller, N. M. Bedford, B. C. Bukowski, and V. S. Thoi, "Flexible 2D Boron Imidazolate Framework for Polysulfide Adsorption in Lithium–Sulfur Batteries," Chem. Mater. (2022), 10.1021/acs.chemmater.2c02324.
- ⁹B. Chen, Z. Yang, Y. Zhu, and Y. Xia, "Zeolitic imidazolate framework materials: Recent progress in synthesis and applications," J. Mater. Chem. A 2, 16811–16831 (2014).
- ¹⁰J. Davis et al., "Manuscript in preparation," (2023).
- ¹¹S. Banerjee, J. M. Gorham, P. Beccar-Varela, H. G. Hackbarth, M. A. Siegler, N. Drichko, J. T. Wright, N. M. Bedford, and V. S. Thoi, "Atomically Dispersed CuN x Sites from Thermal Activation of Boron Imidazolate Cages for Electrocatalytic Methane Generation," ACS Appl. Energy

Mater., acsaem.2c01174 (2022).

- ¹²K. Momma and F. Izumi, "VESTA 3 for three-dimensional visualization of crystal, volumetric and morphology data," J. Appl. Crystallogr. 44, 1272– 1276 (2011).
- ¹³M. Andersson, J. Hedin, P. Johansson, J. Nordström, and M. Nydén, "Coordination of Imidazoles by Cu(II) and Zn(II) as Studied by NMR Relaxometry, EPR, far-FTIR Vibrational Spectroscopy and Ab Initio Calculations: Effect of Methyl Substitution," J. Phys. Chem. A **114**, 13146–13153 (2010).
- ¹⁴M. R. Ryder, B. Civalleri, T. D. Bennett, S. Henke, S. Rudić, G. Cinque, F. Fernandez-Alonso, and J.-C. Tan, "Identifying the Role of Terahertz Vibrations in Metal-Organic Frameworks: From Gate-Opening Phenomenon to Shear-Driven Structural Destabilization," Phys. Rev. Lett. **113**, 215502 (2014).
- ¹⁵A. F. Möslein and J.-C. Tan, "Vibrational Modes and Terahertz Phenomena of the Large-Cage Zeolitic Imidazolate Framework-71," J. Phys. Chem. Lett. **13**, 2838–2844 (2022).
- ¹⁶V. I. Isaeva, K. E. Papathanasiou, and L. M. Kustov, "Zeolite-Like Boron Imidazolate Frameworks (BIFs): Synthesis and Application," Crystals **10**, 617 (2020).
- ¹⁷G. Kumari, K. Jayaramulu, T. K. Maji, and C. Narayana, "Temperature Induced Structural Transformations and Gas Adsorption in the Zeolitic Imidazolate Framework ZIF-8: A Raman Study," J. Phys. Chem. A **117**, 11006– 11012 (2013).
- ¹⁸S. Salama and T. G. Spiro, "Resonance Raman spectra of cobalt(II)imidazole complexes: Analogs of the binding site of cobalt-substituted zinc proteins," J. Am. Chem. Soc. **100**, 1105–1111 (1978).

Raman scattering spectra of Boron Imidazolate Frameworks containing paramagnetic ions

Jackson Davis¹, Soumyodip Banerjee², Pilar Beccar-Varela², V. Sara Thoi^{2, 3}, and Natalia Drichko¹

¹Department of Physics and Astronomy, Johns Hopkins University, Baltimore, Maryland 21218, USA

²Department of Chemistry, Johns Hopkins University, Baltimore, Maryland 21218, USA ³Department of Materials Science and Engineering, Johns Hopkins University, Baltimore, Maryland 21218, USA

Abstract

We present a Raman scattering spectroscopic study of boron imadozolate metal-organic frameworks (BIFs) with a number of paramagnetic ions in a wide frequency range from 25 to 200 cm⁻¹, which covers local vibrations of the linkers and well as collective lattice vibrations. We show that the spectral region above 800 cm⁻¹ belongs to the local vibrations of the linkers, which have the same frequencies for the studied BIFs without any dependence on the structure of the BIFs, and are easily interpreted based on the spectra of imadozolate linkers. In contrast, collective lattice vibrations, observed below 150 cm⁻¹, show distinction between cage and two-dimensional BIFs structures, with a weak dependence on the metal node. We identify the range of vibrations around 200 cm⁻¹, which are distinct for each MOF, depending on a metal node. Our work demonstrated the energy hierarchy in the vibrational response of BIFs.

1 Introduction

Much of the study of metal-organic frameworks (MOFs) in recent years has focused on their tunability and porosity. Since MOF structures can include magnetic ions or clusters connected by organic linkers, a possibility of achieving interesting magnetic states in MOFs was recently discussed [Thorarinsdottir2020, MinguezEspallargas2018]. Most of the recent studies of magnetic properties were limited by basic magnetization and magnetic susceptibility measurements. In order to study magnetism in these materials we will need to employ spectroscopies, such as neutron scattering and magnetic Raman scattering. In fact, magnetic Raman scattering has demonstrated its ability to probe the spectrum of magnetic excitations in organic magnetic materials [Hassan2018] where neutron scattering is challenging to due weak signals and presence of hydrogen in the materials. In order to use Raman scattering spectroscopy as a tool to study different MOF structures and magnetic response, we need to obtain information about energy scales of all the other excitations; we must identify what part of the acquired spectroscopic information is related to the collective lattice modes, and what part is related to the linker vibrations. Vibrational Raman scattering has been widely used as a characterization tool for MOFs, as the vibrational modes within the organic ligands and between the ligands and the metal ions tend to produce sharp, easily identifiable peaks in Raman spectra.

In this manuscript, we present our vibrational Raman scattering studies of a range of MOFs which share the same linkers, but have different paramagnetic metal ions and structures. We aim to understand the hierarchy of the energy scales we observe in the very rich spectra of MOFs, and the efficient ways to interpret the spectral features. We show that we can identify the linker vibrations that are independent of the metal ions environment, while the vibrations of the metal environment are sensitive to the substitution of a metal atom. We further demonstrate that the lattice modes of MOFs are fingerprint of their structures.



Figure 1: Structures of Ni and Co BIFs. (a) Cu BIF cage structure. Cu: blue, C: brown, N: gray, O: red, B: green. H atoms omitted for clarity. (b) Co BIF layer, viewed along the out-of-plane direction. Co: purple, C: brown, N: gray, O: red, B: green. H atoms omitted for clarity. (c) Cu BIF structure showing B³⁺ linking three square planar Cu environments. Spherical complex in background is disordered solvent in the cavities of the BIF. Cu: blue, C: brown, N: gray, O: red, B: green. H atoms omitted for clarity. (d) Octahedral Co environment in Co BIF. Co: purple, C: brown, N: gray, H: pink.

All MOF materials studied here belong to the class of boron imidazolate frameworks (BIFs), which consist of metal ions coordinated by a boron imidazolate ligand. We present Raman spectra of four different BIFs with paramagnetic ions Co, Cu, Zn, and Ni as the metal cations. These BIFs show two distinct structures: Cu- and Zn-BIFs possess a cage-like structure [Zhang2015], Co-BIF and Ni-BIF possess a 2D layered structure [Banerjee2022]. Cage BIFs show topologies similar to zeolites or zeolitic imidazolate frameworks (ZIFs). In ZIFs, each metal cation bonds to one nitrogen of four different imidazolate rings, creating a tetrahedral metal environment, and these linked tetrahedra form a porous 3D network of connected cages. In cage BIFs, one N on the imidazolate ring binds to a metal cation, while the other binds to a B^{3+} cation. For instance, in caged Cu BIF, pictured in Fig. 1a, the metal cations have an environment of four coplanar N atoms from four different imidazolate rings, while one oxygen from one H_2O weakly binds to the metal in the out-of-plane direction, creating a low symmetry environment for the metal atom compared to standard inorganic oxides. In 2D layered BIFs, no cages are formed at all, and metal ions are arranged in a 2D hexagonal lattice (see Co atoms in Fig. 1b), with layers alternating along the crystallographic c axis. In these BIFs, as illustrated for Co-BIF, an octahedral N environment of higher symmetry is formed, as the metal binds to 6 imidazolate rings, as shown in Fig. 1d. The boron cations connect three of these metal-imidazolate complexes, as seen in Fig. 1c. Because of this, the exchange path between metal centers is through not only one imidazolate ring, as in ZIFs, but follows an extended Me-Im-B-Im-Me path. This extended exchange path leds to an extremely low magnetic exchange energy between magnetic metal centers.

Our work demonstrates that, despite of the differences in crystal structures, the Raman vibrations of the

imidazolate linkers observed above 800 cm⁻¹ are similar for these MOFs. In contrast, the lattice vibrations observed below 100 cm⁻¹ are fingerprints of the structure. The intermediate frequencies in the range of 250-400 cm⁻¹ belong to the Raman vibrations of the metal environment and depend on metal cation identity. These results demonstrate the distinct energy scales of vibrations of MOFs of different origins. This fact can allow for an easy interpretation of the vibrational features of these compounds.

2 Experimental

MOFs were synthesized following various literature procedures for Zn BIF [Wen2017], Cu BIF [Banerjee2022a], and Co and Ni BIF [Banerjee2022].

Raman spectra were measured using a micro-Raman option of a T64000 Horiba-Jobin-Yvon spectrometer equipped with an Olympus microscope and a LN₂ cooled CCD. Spectra were excited with the 514.5 nm line of a Coherent Innova 70C laser, with the power kept below 500 μ W for a probe of 2 μ m in diameter to avoid heating the sample. Spectra were measured at room temperature with a spectral resolution of 2 cm⁻¹ (low-energy region) and 6 cm⁻¹ (Ni, Zn, and Cu in high energy region).

Background signals of stray laser light were subtracted manually from the Co, Cu, and Ni BIF spectra to highlight the narrow vibrational mode peaks. A Lorentzian peak centered at 0 cm⁻¹ was used to approximately model the background to be subtracted. In Zn BIF, a broad background was subtracted by comparison to the spectra of pure imidazolate.

3 Results and Discussion

Measured Raman spectra of Co BIF, Cu BIF, Ni BIF, and Zn BIF are shown in two different regions in Figs. 2 and 3. The 500-1700 cm⁻¹ region in Fig. 2 contains the expected vibrational modes of imidazolate and displays preliminary band assignments, which are summarized in Table 1. The 0-500 cm⁻¹ region in Fig. 3 contains low-energy lattice modes below 100 cm⁻¹ and vibrational modes of metal environments above.

The Raman vibrations of imidazolate linkers are expected in the 800-1600 cm⁻¹ spectral range based on Raman spectra of ZIFs [**Hadjiivanov2021**]. Raman spectra of the four different BIFs show very similar frequencies of the majority of the molecular vibrations in the imidazolate ligand, despite the fact that they show two different crystal structures and different metal nodes. It is in agreement with the expectation that the internal structure of the ligand remains unchanged between these MOFs. A comparison to previously reported Raman scattering spectra of ZIF-8 [**Hadjiivanov2021**] reveals a direct correspondence between molecular vibrations of imidazolate in ZIF and BIF structures and is taken as a basis for our interpretation of the vibrational spectra of BIFs. Table 1 summarizes the frequencies of 8 molecular vibrations, which are consistent with previously reported band assignments for imidazolate ligand. We mark these assignments in the Raman spectra of the BIFs shown in Fig. 2.

The most intense modes in the spectral region of $800-1000 \text{ cm}^{-1}$ are bending vibrations of C-H bonds, which are out-of-plane with respect to the plane of the imidazolate ring. These three bands are found at very similar frequencies for all measured BIFs and close to the reported frequencies in ZIF-8. The C-H bonds are the farthest away from the metals, so one would expect that their frequencies are not strongly dependent on the metal nodes.

The spectral range between 1000 and 1500 cm⁻¹ contains 4 stretching vibrations of C-N bonds as well as a wagging vibration of N-H. Though the positions of the two lowest bands are shifted by 70 cm⁻¹ to higher frequencies compared with the ZIF-8 spectra, the spacing of 40 cm⁻¹ between them and their relative intensities are consistent with reported ZIF spectra. The C-N stretching vibration in the range from 1334-1343 cm⁻¹ displays a shift to lower frequencies of 50 cm⁻¹. These minor differences between ZIF and BIF C-N vibrations can be attributed to the fact that the two N on an imidazolate ring bind to one metal ion and one B, rather than two Zn ions as in ZIFs. Hence, the molecular vibrations that involve the N are expected to differ qualitatively between ZIF and BIF spectra, though not between BIFs themselves. In contrast, other molecular vibrations (such as C-H bending) display more consistency between ZIF and BIF spectra due to their relative isolation from the environment external to the imidazolate ring.

The reported bending vibration of the methyl group in ZIF-8 is absent in BIF spectra since the imidazolate rings in the BIFs have no capping methyl group. The total suppression of the strong imidazolate ring



Figure 2: Raman spectra of Cu-, Co-, Zn-, and Ni-based BIFs in the range of ligand vibrational modes. Spectra have been shifted by a constant for clarity. Background signals were manually subtracted for visual clarity and spectra were scaled by a constant to normalize to the ν (CN) modes in the 1200-1250 cm⁻¹ range.

breathing mode can be a result of the lower symmetry (the absence of mirror symmetry) in the linker in BIF structures, that comes from imidazolate binding to one B and one metal ion, rather than two metal ions as in ZIFs, or a result of a reduction of electronic density on the imidazolate ring.

Raman mode	ZIF-8 Band (cm^{-1})	Co BIF	Cu BIF	Zn BIF	Ni BIF
δ (CH) out-of-plane	834	831	853	weak	841
δ (CH) out-of-plane (C4-C5)	945	939	946	960	945
δ (CH) out-of-plane (C2)	1023	1018	1020	1021	1021
ν (C5-N)	1143	1214	1215	1216	1210
ν (C-N)	1182	1258	1252	1259	1247
ω (N-H)	1312	1316	1314	1311	1309
ν (C5-N)	1385	1343	1335	1333	1336
ν (C2-N)	1507	1505	1515	1517	1510

Table 1: Raman band assignment for ZIF-8 compared to band assignment for Co, Cu, Zn, and Ni BIF, using mode nomenclature from [Hadjiivanov2021]. δ : bend, ν : stretch, ω : wag.

The spectral range of 150-300 cm⁻¹ is the region of metal-ligand vibrations; their frequency would be dependent both on the metal and on its coordination. [Andersson2010]. In particular, literature data suggest stretching vibrations of Cu-N in the octahedral environment is at 280-290 cm⁻¹, Zn in tetrahedral environment is at 207 cm⁻¹. [Andersson2010]. Vibrations at about 250 cm⁻¹ therefore belong to the N-metal vibration, and have frequencies that varyu depending on the metal ion.

Fig. 3 presents the low frequency spectra of the BIF MOFs. Typically for molecular crystals the region below 100 cm^{-1} corresponds to lattice vibrations, which would depend on the structure of the MOFs. While to the best of our knowledge, no spectroscopic information on the lattice modes of BIFs has been published, the lattice "collective" modes of ZIFs were studied by THz spectroscopy, neutron scattering, and DFT



Figure 3: Raman spectra of Cu-, Co-, Zn-, and Ni-based BIFs in the low energy region. Spectra have been shifted by a constant for clarity. Background signals were manually subtracted for visual clarity.

calculations, and were also found below 100 cm⁻¹ [**Ryder2014**, **Moslein2022**]. In our experimental data, we find that two low-frequency vibrations of the cage Cu and Zn BIFs occur at similar frequencies, while 2D Ni and Co BIFs have similar low-frequency spectra distinct from the cage BIFs. Frequencies of the observed lattice vibrations are summarized in Table 2, along with a comparison to the DFT results for ZIF-8. This demonstrates a distinct dependence of the lattice mode spectra on the structure of the MOFs, showing that the lattice vibrations are fingerprints of a particular lattice structure, and not the chemical environment. Further, we find that the lattice modes observed in the spectra for the two cage BIFs, Cu and Zn, are similar to Raman-active lattice modes in the calculated DFT spectra of ZIF-8. These include a strong mode at 33.36 cm⁻¹, assigned to a symmetric 4-membered ring gate opening, and a mode at 64.61 cm⁻¹, assigned to a 4-membered ring shearing [**Ryder2014**]. The strongest observed modes in our Zn and Cu BIF spectra occur at similar frequencies and thus support a similarity between the porous framework geometry of ZIF-8 and the 3D cage geometry of these two BIFs. The 2D layered BIFs, on the other hand, do not display any similarity to calculated THz modes of ZIFs, which is consistent with the more significant structural differences.

ZIF-8 DFT	Zn BIF	Cu BIF	Co BIF	Ni BIF
33.36	34	35		
—			52	53
64.61	62	58		
			77	74

Table 2: Frequencies of observed modes below 100 cm^{-1} for the four BIFs.

The presented comparison between BIF MOFs with different paramagnetic atoms and the literature data on ZIFs demonstrates a separation between the different energy scales related to the different types of vibrations of the MOFs. The higher frequency vibrations are defined by the ligands, and are basically similar between MOFs with the same ligands but different structures. It makes it possible to interpret vibrational spectra in that frequency region by a comparison to the spectra of the ligands. The spectral region between approximately 100 and 400 cm⁻¹ is dominated by the vibrations of the metal environment. It depends on the metal atom, but shows some consistency between BIFs with different metals. The region of the lattice vibrations of MOFs below 100 cm⁻¹ shows the fingerprint of a certain structure, either cage-like or 2D MOFs, with some small variations as a result of different metal atoms.

4 Conclusions

In this work, we have demonstrated a stability of the frequencies of Raman-active vibrational modes of imidazolate ligands between four different BIFs with different structures and paramagnetic metals. We show that the low-energy region of the spectra demonstrate a consistency in lattice modes of isostructural BIFs. The modes of the cage-like BIFs show frequencies similar to the calculated lattice modes for ZIFs, while 2D BIFs have distinctly different lattice modes spectrum. The bands in the 100-400 cm⁻¹, which likely correspond to vibrations of the metal environments, display the expected variation between BIFs with different metal ions. The consistency of lattice modes and ligand vibrations provides a way to understand and assign their spectra without full calculations of vibrational response performed for each MOF structure.

5 Acknowledgements

Acknowledgement is made to the donors of the American Chemical Society Petroleum Research Fund for partial support of this research. We acknowledge the support of NSF Award No. DMR-2004074. S. B., P. B.-V., and V. S. T. acknowledge support by the U.S. Department of Energy (DOE), Office of Science, Office of Basic Energy Sciences, Catalysis Science program, under Award DE-SC0021955. P. B-V. thanks the Dean's ASPIRE grant from the Office of Undergraduate Research, Scholarly and Creative Activity at Johns Hopkins University. We further acknowledge Professor Tyrel McQueen and Dr. Veronica Stewart (Department of Chemistry, Johns Hopkins University), for their assistance in obtaining magnetic susceptibility data.